



"USP BULGARIA" LTD.

Bulgaria, Sofia

1582, jk "Druzhba" 2

Blvd "Prof.Tsvetan Lazarov" № 90

+380503115715

Clearcoat SP40 plus MS 2+1

This is another clearcoat on Medium Solid system characterized by high hardness, resistance to UV radiation, which is also highly resistant to harmful weather conditions. It has very good resistance to stone chipping. Lacquer coating does not flake even at the strong beats. Works with all types of basecoat and the water basecoats. There is a slow, normal and rapid version of the hardener. Product is very easy to apply by spraying two full layers in intervals 5-10 minutes, very easy to give polish.

CONTENTS OF VOLATILE ORGANIC COMPOUNDS:

VOC = 521 g/L without hardener

VOC = Max. incl. VOC in the finished product for use with a hardener and diluent do not exceed 626 g/L

ATTENTION!!!

Clearcoat MS PLUS complies with the standard of VOC set out in EU Directive

Qualified for CAT B/5

GLOSS: Output gloss: 96.

COLOR: Colorless



For professional use only

MIXING SUGGESTIONS: Clearcoat MS PLUS :Hardener MS PLUS = 2:1

Acrylic Thinner EXLAK STANDARD – 10-15% weight of clearcoat with hardener.

APPLICATION LIFE WHEN MIXED WITH HARDENER: Using the standard hardener: about 1 hour at 20°C

CONDITIONS OF APPLYING: Spraying viscosity, spray gun nozzle, pressure:

DIN 4/20°C 17-18 s, Ø1.2.1.4mm, 3.4 bar

After adding 10% - 15 % thinner for acrylic products:

DIN 4/20°C 16.17 s, Ø1.3.1.4mm, 3.4 bar

RULES OF PROCEDURE WHEN APPLYING: Clearcoat MS PLUS is applied to a previously imposed and dried basecoat layer. Spray system: 2 full layers at intervals of 5-10 minutes between coats.

DRYING TIME: Dust-free: 10 min at 20°C or 5 min at 60°C

HARDNESS UTILITY: 14 hours at 20°C at 45 min at 60°C.

Hardness after 14 days tested in accordance with PN-EN ISO 1522 Persoza Pendulum - 326

Fully hardened coating – after 4 days.

TIME AND STORAGE CONDITIONS: Store in a cool, dry place, away from sources of ignition and heat. Avoid exposure to sunlight. Warranty 12 months.

CLEANING EQUIPMENT: Thinner for acrylic products, nitro

BHP REGULATIONS: See Safety Data Sheet for this product

PACKAGING: Clearcoat is supplied in individual containers with a capacity of 1.0 i 5.0L

Specific weight: 984 g/L